


R E M A R K S

The cross reference to related applications has been inserted.
A new set of claims for the divisional application is being
provided hereby, and the Abstract has been amended. Entry and
Allowance are respectfully requested.

Respectfully submitted,

HIROYUKI KOSOKABE ET AL



Kurt Kelman, Reg. No. 18,628

Allison C. Collard, Reg. No. 22,532

Edward R. Freedman, Reg. No. 26,048

Attorneys for Applicants

COLLARD & ROE, P.C.
1077 Northern Boulevard
Roslyn, New York 11576
(516) 365-9802

I hereby certify that this correspondence is being deposited with the United States Postal Service as
Express Mail in an envelope addressed to: MAIL STOP Division, Commissioner for Patents, P.O. Box
1450, Alexandria, VA 22313-1450, on July 15, 2003 _____

Express Mail: EV 324 140 323 US



Maria Guastella

Marked-up copy of changes:

Please amend the Abstract as follows: --

ABSTRACT

A tungsten sealing glass for use in a fluorescent lamp, said glass having a composition of, by mass percent, 65-76% SiO_2 , 10-25% B_2O_3 , 2-6% Al_2O_3 , 0.5-5.8% $\text{MgO} + \text{CaO} + \text{SrO} + \text{BaO} + \text{ZnO}$, 3-8% $\text{Li}_2\text{O} + \text{Na}_2\text{O} + \text{K}_2\text{O}$, 0.01-4% $\text{Fe}_2\text{O}_3 + \text{CeO}_2$, 0.1-5% TiO_2 , [0]0.1-10% TiO_2 + Sb_2O_3 + PbO , and 0-2% ZrO_2 , wherein $\text{Na}_2\text{O}/(\text{Na}_2\text{O} + \text{K}_2\text{O}) \leq 0.6$.